



# BODY HIGH HEAT BRAKE CALIPER PAINT SPRAY

Technical Data Sheet No 836

VOC compliant with the regulations

Silicone Aerosol Paint

Recommended for the painting of objects which are exposed to temperatures of up to 300°C

Excellent results

## General Technical Description

2-3 passes

Dust free 10min at 23 °C

## Surface

For the painting of metal objects which are exposed to temperatures of up to 300°C

## Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST

Make sure the surface is air dried rather than wiped dry



Make sure you always use appropriate face protection and good ventilation

**Product Application:** »» Apply on objects which are exposed to temperatures up to 300°C. Apply two to three medium coats necessary to cover the area waiting 5-10 mins in between each coat. Each coat should appear uniform and dry before the next one is applied.



Shake well before using



2-3 coats approximately 20-30 microns



Dust free 10 min at 23°C



Full hardness within 24 hours

**Flash Point:**  
-97°C

**Specific Gravity:**  
1,019 g/cm<sup>3</sup>

**Solid Content (No thinner):**  
35% Weight

### VOC (2004/42/EC)

This is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 770g/L. 2004/42/IIIB(e)(840)770

**Theoretical Coverage:**

-

**Cleaning of equipment:**

-

### Remarks:

- Always try to use the product in accordance with the specifications provided.
- It can be used by countries that do not adopt the VOC legislation as well.
- Shake thoroughly before use.
- Shake for 2-3 mins after agitator ball has started to rattle. After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action.
- Spray at a distance of 20-30 cm thinly applied coats build up within 3-5 min intervals to achieve best results. Leave for 24 hours to harden.
- Optimum operating temperature range 10-25 °C.

### Shelf life:

- Up to 36 months unused spray.
- +5 to +25 °C

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.