



969 ANTICORROSIVE PRIMER

Technical Data Sheet No 113

VOC compliant with the regulations

1K Alkyd Based System

High quality, quick drying

Excellent anticorrosion protection

Zinc Chromate free

General Technical Description



Mix BODY 969 ANTICORROSIVE PRIMER with BODY 767 EXTRA NITRO THINNER

Air dry 5-6h / 23°C (73°F) panel temperature

Surface

On old, sanded paint work

Metal surfaces

OEM surfaces

Clean and sanded steel panels

HB Body Polyester Fillers

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL/BODY 771 ANTISIL FAST.

Make sure the surface is first wiped dry and then air dried



Make sure you always use appropriate face protection and good ventilation

Product Application: Anticorrosive primer 2 passes »» Apply in thin layers over sanded areas only



Mix well BODY 969 ANTICORROSIVE PRIMER



10 min / 23°C (73°F) Final flash off time

Flash Point:
30°C / 86°F

Remarks:

- Allow for additional time for combi spray booths to reach the desired temperature
- Application only with the recommended hardeners and solvents
- It could be used by countries that do not adopt the VOC legislation as well.
- Do not use at temperatures below 15°C (59°F).
- Should be applied on sanded areas only
- ZINC CHROMATE FREE



10% BODY 767 NITRO EXTRA THINNER



Non force dry
60-80µm (2.4 - 3.2mil)
5-6h / 23°C (73°F)

Specific Gravity:
1.50 g/cm³

Solid Content (No thinner):
72% Weight



25% BODY 767 EXTRA NITRO THINNER
18-23 s
DIN 4 @ 20°C (68°F)



- HB BODY Color Solutions Basecoat
- HB BODY Color Solutions 2K
- HB BODY Clears

VOC (2004/42/EC)
This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 540 g/L. The VOC content in the ready for use form of this product is 410 g/L.
2004/42/IIB(c)(540)410



Compliant Spray gun
1.5-1.8 mm
2-3 bar (29-44psi)
inlet pressure
2x coat = 60-80 micron
(2.4 - 3.2mil)



Always wear protective equipment

Theoretical Coverage:
7 m² / l at 60 micron (2.4 mil) dry film thickness

Storage Shelf life:

- Store in a cool place (+5°C - +25°C) (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers



HVLP 1.5-1.7 mm
2-3 bar (29psi)
inlet pressure
2x coat = 60-80 micron
(2.4 - 3.2mil)



Follow the application instructions mentioned in this TDS

Cleaning of equipment:
Clean after final use with BODY 767 EXTRA NITRO THINNER

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 4/2018, January 2018