



BODY 930 BITUMEN UNDERBODY COATING

Technical Data Sheet No 702

General Technical Description

Thixotropic material based on caoutchouc and tar

Remains elastic and it is adhered perfectly

Provides excellent underbody protection

Dries quickly

Surface

Underbody parts

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST

Make sure the surface is first wiped dry and then air dried



Make sure you always use appropriate face protection and good ventilation

Product Application:

»» It is applied on the underneath parts of the car. Applicable with a brush or a spray gun at a pressure of 5-6 bar (73-87 psi).



Drying time
2 - 6h / 23°C (73°F)



Protect from humidity



Always close tin after use



Always wear protective equipment



Follow the application instructions mentioned in this TDS



Shake well before using: 2-3min



Apply with spray gun:
Long nozzle :4-5mm
Pressure 5-6 bar (73-87 bar)



10-15min / 23°C (73°F)
Final Flash off time

Flash Point:
<0°C (32°F)

Specific Gravity:
1.07 g/cm³

Solid Content (No thinner):
58-62% Weight

VOC (2004/42/EC)
This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 350 g/L.
2004/42/IIB(e)(840)350

Theoretical Coverage:
4 - 5 m² / l at 100 µm (4 mil)
dry film thickness

Cleaning of equipment:
Clean after final use with:
Body 740 ACRYL NORMAL /
Body Extra Nitro Thinner

Remarks:

- Allow for additional time for combi spray booths to reach the desired temperature
- Best results when used with HB BODY PRODUCTS.
- It can be used by countries that do not adopt the VOC legislation as well.

Storage shelf life:

- Store in a cool place +5°C - 25°C (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers.

This is a thixotropic material based on caoutchouc and tar. It is applied on the underneath parts of the car. It protects from rust, noise and it is highly resistant to road stone chipping. It remains elastic and it is adhered perfectly. It dries quickly and it cannot be painted because it contains asphalt. It can be applied with either a brush or a spray gun at 5-6 bar pressure

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 2 / 2017, April 2017